# **Technical Data Sheet**

# Schulablend LUCENT PC/ABS-1218EFL BLK



Polycarbonate + ABS

# **Product Description**

Polycarbonate + ABS, Easy Flow Injection GradeColors AvailableAdd "R" for Added ReleaseAdd "U" for UV Stablilized

# **Regulatory Status**


For regulatory compliance information, see LUCENT PC/ABS-1218EFL BLK <u>Product Stewardship Bulletin (PSB)</u> and Safety Data Sheet (SDS).

Status Commercial: Active
Availability North America
Processing Method Injection Molding

Attribute Good Flow

Appearance Colors Available

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (260 °C/5.0 kg)	18	g/10 min	ASTM D1238
Density - Specific Gravity	1.13	g/cm³	ASTM D792
Mechanical			
Tensile Strength at Yield	55.8	MPa	ASTM D638
Flexural Modulus	2260	MPa	ASTM D790
Tensile Elongation at Break	>140	%	ASTM D638
Flexural Strength	86.2	MPa	ASTM D790
Impact			
Notched Izod Impact, (3.18 mm)	640	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	110	°C	ASTM D648



	Nominal		
njection Parameters	Value	Units	
Drying Temperature	82 to 99	°C	
Suggested Max Moisture	<0.020	%	
Nozzle Temperature	249 to 277	°C	
Processing (Melt) Temp	238 to 277	°C	
Front Temperature	238 to 271	°C	
Middle Temperature	238 to 271	°C	
Rear Temperature	232 to 260	°C	
Injection Rate	Moderate- Fast		
Back Pressure	<1.03	MPa	
Mold Temperature	60 to 82	°C	

#### **Notes**

These are typical property values not to be construed as specification limits. The typical values for this product may have been tested on a natural grade.

## **Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

### **Company Information**

For further information regarding the LyondellBasell company, please visit <a href="http://www.lyb.com/">http://www.lyb.com/</a>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

### **Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.