

Technical Data Sheet

Icorene 9031 BA8

Polyethylene
LyondellBasell Industries
Rotomolding

General			
Features	• Expandable	• Foamable	• Good Adhesion
Appearance	• Natural Color		
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density ¹	0.140 g/cm³	0.140 g/cm³	ASTM D1622
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Thermal Conductivity	0.25 Btu·in/hr/ft²/°F	0.036 W/m/K	ASTM C518

Notes

¹ Final

Notes

These are typical property values not to be construed as specification limits.