

Technical Data Sheet

Qr Resin QR-3000

Polyethylene Terephthalate
LyondellBasell Industries
Engineering Plastics

General			
Features	• Chemical Resistant	• Semi Crystalline	
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.30	1.30 g/cm ³	ASTM D792

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	7000 psi	48.3 MPa	ASTM D638
Flexural Modulus	300000 psi	2070 MPa	ASTM D790
Flexural Strength (Break)	12000 psi	82.7 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.0 ft·lb/in	53 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	150 °F	65.6 °C	
264 Psi (1.8 Mpa), Unannealed	140 °F	60.0 °C	

Technical Data Sheet

Qr Resin QR-3000

Polyethylene Terephthalate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 8.0 hr	3.0 to 8.0 hr
Drying Time, Maximum	8.0 hr	8.0 hr
Rear Temperature	460 to 490 °F	238 to 254 °C
Middle Temperature	470 to 500 °F	243 to 260 °C
Front Temperature	480 to 510 °F	249 to 266 °C
Nozzle Temperature	470 to 500 °F	243 to 260 °C
Processing (Melt) Temp	480 to 510 °F	249 to 266 °C
Mold Temperature	150 to 190 °F	66 to 88 °C

Notes

These are typical property values not to be construed as specification limits.