

Technical Data Sheet

# Schulaketon MV FC

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics

## Product Description

Medium viscosity aliphatic Polyketone for food contact applications

## General

|                     |             |                     |
|---------------------|-------------|---------------------|
| Processing Method   | • Extrusion | • Injection Molding |
| Resin ID (ISO 1043) | • PK        |                     |

| Physical                                    | Nominal Value (English)    | Nominal Value (SI)         | Test Method     |
|---------------------------------------------|----------------------------|----------------------------|-----------------|
| Density                                     | 1.24 g/cm <sup>3</sup>     | 1.24 g/cm <sup>3</sup>     | ISO 1183/A      |
| Melt Volume-Flow Rate (MVR) (240°C/2.16 Kg) | 6.0 cm <sup>3</sup> /10min | 6.0 cm <sup>3</sup> /10min | ISO 1133        |
| Mechanical                                  | Nominal Value (English)    | Nominal Value (SI)         | Test Method     |
| Tensile Modulus                             | 203000 psi                 | 1400 MPa                   | ISO 527-1/1A/1  |
| Tensile Stress (Yield)                      | 8700 psi                   | 60.0 MPa                   | ISO 527-2/1A/50 |
| Tensile Strain (Yield)                      | 20 %                       | 20 %                       | ISO 527-2/1A/50 |
| Flexural Modulus <sup>1</sup>               | 218000 psi                 | 1500 MPa                   | ISO 178         |
| Flexural Stress <sup>1</sup>                |                            |                            | ISO 178         |
| 9.0% Strain                                 | 8700 psi                   | 60.0 MPa                   |                 |
| 3.5% Strain                                 | 8700 psi                   | 60.0 MPa                   |                 |
| Impact                                      | Nominal Value (English)    | Nominal Value (SI)         | Test Method     |
| Charpy Notched Impact Strength              |                            |                            | ISO 179/1eA     |
| -40°F (-40°C)                               | 2.4 ft·lb/in <sup>2</sup>  | 5.0 kJ/m <sup>2</sup>      |                 |
| 73°F (23°C)                                 | 10 ft·lb/in <sup>2</sup>   | 22 kJ/m <sup>2</sup>       |                 |
| Charpy Unnotched Impact Strength            |                            |                            |                 |
| -40°F (-40°C)                               | No Break                   | No Break                   | ISO 179         |
| 73°F (23°C)                                 | No Break                   | No Break                   | ISO 179/1eU     |
| Thermal                                     | Nominal Value (English)    | Nominal Value (SI)         | Test Method     |
| Deflection Temperature Under Load           |                            |                            |                 |
| 66 Psi (0.45 Mpa), Unannealed               | 336 °F                     | 169 °C                     | ISO 75-2/Bf     |
| 264 Psi (1.8 Mpa), Unannealed               | 171 °F                     | 77.0 °C                    | ISO 75-2/Af     |
| Vicat Softening Temperature                 |                            |                            |                 |
| --                                          | 369 °F                     | 187 °C                     | ISO 306/B50     |
| --                                          | 417 °F                     | 214 °C                     | ISO 306/A50     |
| RTI Elec                                    |                            |                            | UL 746B         |
| 0.031 In (0.8 Mm)                           | 122 °F                     | 50.0 °C                    |                 |
| 0.06 In (1.6 Mm)                            | 122 °F                     | 50.0 °C                    |                 |
| 0.12 In (3.0 Mm)                            | 122 °F                     | 50.0 °C                    |                 |
| RTI Imp                                     |                            |                            | UL 746B         |
| 0.031 In (0.8 Mm)                           | 122 °F                     | 50.0 °C                    |                 |
| 0.06 In (1.6 Mm)                            | 122 °F                     | 50.0 °C                    |                 |
| 0.12 In (3.0 Mm)                            | 122 °F                     | 50.0 °C                    |                 |
| RTI Str                                     |                            |                            | UL 746B         |
| 0.031 In (0.8 Mm)                           | 122 °F                     | 50.0 °C                    |                 |
| 0.06 In (1.6 Mm)                            | 122 °F                     | 50.0 °C                    |                 |
| 0.12 In (3.0 Mm)                            | 122 °F                     | 50.0 °C                    |                 |

Technical Data Sheet

## Schulaketon MV FC

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics

| Electrical                              | Nominal Value (English) | Nominal Value (SI) | Test Method                      |
|-----------------------------------------|-------------------------|--------------------|----------------------------------|
| Surface Resistivity                     | > 1.0E+15 ohms          | > 1.0E+15 ohms     | IEC 60093                        |
| Volume Resistivity                      | > 1.0E+13 ohms·m        | > 1.0E+13 ohms·m   | IEC 62631-3-1                    |
| Comparative Tracking Index (Solution A) | 600 V                   | 600 V              | IEC 60112                        |
| Flammability                            | Nominal Value (English) | Nominal Value (SI) | Test Method                      |
| Burning Rate                            |                         |                    |                                  |
| 0.0787 In (2.00 Mm)                     | < 3.9 in/min            | < 100 mm/min       | ISO 3795                         |
| 0.0787 In (2.00 Mm)                     | < 3.9 in/min            | < 100 mm/min       | FMVSS 302                        |
| Flame Rating                            |                         |                    |                                  |
| 0.031 In (0.8 Mm)                       | HB                      | HB                 | UL 94                            |
| 0.06 In (1.6 Mm)                        | HB                      | HB                 | UL 94<br>IEC 60695-11-10,<br>-20 |
| 0.13 In (3.2 Mm)                        | HB                      | HB                 | UL 94                            |
| 0.03 In (0.8 Mm)                        | HB                      | HB                 | IEC 60695-11-10,<br>-20          |
| 0.12 In (3.0 Mm)                        | HB                      | HB                 | IEC 60695-11-10,<br>-20          |
| Glow Wire Flammability Index            |                         |                    | IEC 60695-2-12                   |
| 0.06 In (1.5 Mm)                        | 1290 °F                 | 700 °C             |                                  |
| 0.12 In (3.0 Mm)                        | 1290 °F                 | 700 °C             |                                  |
| Glow Wire Ignition Temperature          |                         |                    | IEC 60695-2-13                   |
| 0.06 In (1.5 Mm)                        | 1340 °F                 | 725 °C             |                                  |
| 0.12 In (3.0 Mm)                        | 1340 °F                 | 725 °C             |                                  |

Technical Data Sheet

## Schulaketon MV FC

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics



| Injection              | Nominal Value (English) | Nominal Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature     | 176 °F                  | 80 °C              |
| Drying Time            | 3.0 to 4.0 hr           | 3.0 to 4.0 hr      |
| Suggested Max Moisture | 0.15 %                  | 0.15 %             |
| Processing (Melt) Temp | 437 to 464 °F           | 225 to 240 °C      |
| Mold Temperature       | 140 to 248 °F           | 60 to 120 °C       |

### Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 15 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

### Notes

<sup>1</sup> 0.079 in/min (2.0 mm/min)

### Notes

These are typical property values not to be construed as specification limits.