

Technical Data Sheet

Ferrex GPP20CV04HB BLACK

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight		
Features	• Copolymer	• High Gloss	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.03	1.03 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°c/2.16 Kg)	17 g/10 min	17 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°f (23°c))	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation (Break, 73°f (23°c))	45 %	45 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°f (23°c)	170000 psi	1170 MPa	
Tangent : 73°f (23°c)	186000 psi	1280 MPa	
Flexural Strength (73°f (23°c))	5300 psi	36.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°f (23°c))	2.8 ft·lb/in	150 J/m	ASTM D256
Unnotched Izod Impact (73°f (23°c))	No Break	No Break	ASTM D4812
Gardner Impact (73°f (23°c))	275 in·lb	31.1 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	
264 Psi (1.8 Mpa), Unannealed	130 °F	54.4 °C	

Notes

These are typical property values not to be construed as specification limits.