

Technical Data Sheet

Matrixx FPP3B20CCFDNA

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

FPP3B20CCFDNA is a 20% Glass Fiber Reinforced, Chemically Coupled, Copolymer Polypropylene

General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Features	• Homopolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Mass-Flow Rate (MFR)	6.9 g/10 min	6.9 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	8820 psi	60.8 MPa	ASTM D638
Flexural Modulus	537000 psi	3700 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	2.7 ft·lb/in	150 J/m	ASTM D256

Technical Data Sheet

Matrixx FPP3B20CCFDNA

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	390 to 470 °F	199 to 243 °C
Middle Temperature	390 to 470 °F	199 to 243 °C
Front Temperature	390 to 470 °F	199 to 243 °C
Processing (Melt) Temp	390 to 470 °F	199 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Moderate	Moderate
Back Pressure	< 50.0 psi	< 0.345 MPa
Screw Speed	20 to 60 rpm	20 to 60 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Drying not normally required

Notes

These are typical property values not to be construed as specification limits.