

Technical Data Sheet

Matrixx TPP2B10

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Talc, 10% Filler by Weight		
Features	• Copolymer		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.970	0.968 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4000 psi	27.6 MPa	ASTM D638
Flexural Modulus - Tangent	220000 psi	1520 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.5 ft·lb/in	80 J/m	ASTM D256
Gardner Impact	75.0 in·lb	8.47 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	215 °F	102 °C	
264 Psi (1.8 Mpa), Unannealed	130 °F	54.4 °C	
RTI Str	150 °F	65.6 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Technical Data Sheet

Matrixx TPP2B10

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	350 to 430 °F	177 to 221 °C
Middle Temperature	350 to 430 °F	177 to 221 °C
Front Temperature	350 to 430 °F	177 to 221 °C
Processing (Melt) Temp	390 to 440 °F	199 to 227 °C
Mold Temperature	70 to 120 °F	21 to 49 °C
Injection Rate	Moderate	Moderate
Back Pressure	20.0 to 300 psi	0.138 to 2.07 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Drying not normally required
Injection Booster Pressure: Maximum without flash, 60% of machine maximum, target
Screw Speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.