

Technical Data Sheet

Polyflam RIPP 3625 CS1

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

25% mineral filled flame-retardant PP-Copolymer; without PBDE

General

Filler / Reinforcement	• Mineral, 25% Filler by Weight		
Features	• Copolymer	• Copper Contact Stabilized	• Flame Retardant
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PP/PE-MD25 FR(17+61)		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.39 g/cm³	1.39 g/cm³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	10 cm³/10min	10 cm³/10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	348000 psi	2400 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	2470 psi	17.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.0 %	2.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	3.6 ft·lb/in²	7.5 kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	38 ft·lb/in²	80 kJ/m²	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	192 °F	89.0 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	129 °F	54.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	145 °F	63.0 °C	ISO 306/B50
--	279 °F	137 °C	ISO 306/A50
Ball Pressure Test (221°F (105°C))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Imp			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Str			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Electric Strength ¹			IEC 60243-1
73°F (23°C), 0.0394 In (1.00 Mm), In Oil	1000 V/mil	40 kV/mm	
Comparative Tracking Index	600 V	600 V	IEC 60112

Technical Data Sheet

Polyflam RIPP 3625 CS1

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
Flame Rating			UL 94
0.06 In (1.5 Mm)	V-0	V-0	IEC 60695-11-10, -20
0.12 In (3.0 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1380 °F	750 °C	
0.12 In (3.0 Mm)	1380 °F	750 °C	
Oxygen Index	28 %	28 %	ISO 4589-2

Technical Data Sheet

Polyflam RIPP 3625 CS1

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	392 to 428 °F	200 to 220 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Injection Notes

Mould surface contacting melt should
be of non-corrosive steel (content of chrome > 12%)