

Technical Data Sheet

Polyfort RPP43EU86BK-BK GAPEX HPBLK



Polypropylene Copolymer

Product Description

Polyfort RPP43EU86BK-BK GAPEX HPBLK is a Polypropylene Copolymer Glass Fiber, 43% filled material. Features include: Heat Stabilized.

Attribute	Heat Stabilized
Forms	Pellets
Appearance	Black
Additive	Heat Stabilizer
Filler/Reinforcement	Glass Fiber, 43%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	3.0	g/10 min	ASTM D1238
Density - Specific Gravity	1.25	g/cm ³	ASTM D792
Mechanical			
Tensile Strength, (23 °C)	89.0	MPa	ASTM D638
Flexural Modulus	6400	MPa	ASTM D790
Impact			
Notched Izod Impact			
(23 °C)	140	J/m	ASTM D256
(-23 °C)	790	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	147	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	71 to 82	°C
Nozzle Temperature	232 to 260	°C
Processing (Melt) Temp	221 to 238	°C
Front Temperature	232 to 260	°C
Middle Temperature	227 to 243	°C
Rear Temperature	221 to 238	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 to 0.345	MPa
Mold Temperature	38 to 66	°C
Cushion	5.08 to 12.7	mm