(+) 188 1699 6168 hongrunplastics.com



Dexflex 810

Compounded Polyolefin

Product Description

 $\textit{Dexflex} \ 810 \ \text{is a thermoplastic olefinic elastomer} \ (\text{TPO}) \ that \ \text{offers excellent paintability and processability}.$

Product Characteristics

Status Commercial: Restricted

Test Method used ISO

Availability North America

Processing Methods Injection Molding

Features Paintable, Good Processability

Typical Customer Applications Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.92	g/cm³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	11	g/10 min
Mechanical			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	16.5	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	850	MPa
Note: 80x10x4mm specimen			
Impact			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	16	J
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinka	ge recommendations		

Notes

Typical properties; not to be construed as specifications.