

Technical Data Sheet

Ferrex GPP20CS63HB BLACK

Polypropylene
LyondellBasell Industries
Engineering Plastics

General		
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight	
Additive	• Impact Modifier	
Features	• High Gloss	• Impact Modified
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3600 psi	24.8 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	75 %	75 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	218000 psi	1500 MPa	
Tangent : 73°F (23°C)	234000 psi	1610 MPa	
Flexural Strength (73°F (23°C))	5800 psi	40.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.8 ft·lb/in	96 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	23 ft·lb/in	1200 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	275 in·lb	31.1 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	195 °F	90.6 °C	
264 Psi (1.8 Mpa), Unannealed	125 °F	51.7 °C	

Notes

These are typical property values not to be construed as specification limits.