

Technical Data Sheet

Ferrex GPP35CS33UL-BK

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 36% Filler by Weight		
Additive	• Impact Modifier		
Features	• Good Impact Resistance	• High Gloss	• Impact Modified
Uses	• Electrical Housing	• Housings	• Lawn and Garden Equipment
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.19	1.19 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	150 %	150 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	215000 psi	1480 MPa	
Tangent : 73°F (23°C)	241000 psi	1660 MPa	
Flexural Strength (73°F (23°C))	4800 psi	33.1 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	12 ft·lb/in	610 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact			ASTM D5420
73°F (23°C), 0.125 In (3.18 Mm)	165 in·lb	18.6 J	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	68	68	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	205 °F	96.1 °C	
264 Psi (1.8 Mpa), Unannealed	130 °F	54.4 °C	

Technical Data Sheet

Ferrex GPP35CS33UL-BK

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	200 °F	93 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	390 to 400 °F	199 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 420 °F	210 to 216 °C
Nozzle Temperature	420 to 430 °F	216 to 221 °C
Mold Temperature	115 to 140 °F	46 to 60 °C
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Screw Speed	100 to 150 rpm	100 to 150 rpm
Clamp Tonnage	2.0 to 3.0 tons/in ²	2.8 to 4.1 kN/cm ²
Screw L/D Ratio	20.0:1.0	20.0:1.0
Screw Compression Ratio	2.0:1.0	2.0:1.0

Notes

These are typical property values not to be construed as specification limits.