

Technical Data Sheet

Ferro Pp LPP20BK21NA

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Additive	• Impact Modifier
Features	• Impact Modified
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	3500 psi	24.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	120 %	120 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	216000 psi	1490 MPa	
Tangent : 73°F (23°C)	230000 psi	1590 MPa	
Flexural Strength (Yield, 73°F (23°C))	5300 psi	36.5 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.4 ft·lb/in	75 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	25 ft·lb/in	1300 J/m	ASTM D4812
Gardner Impact	200 in·lb	22.6 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	205 °F	96.1 °C	
264 Psi (1.8 Mpa), Unannealed	130 °F	54.4 °C	

Additional Information	
Filler Content, ASTM D2584: 21%	

Technical Data Sheet

Ferro Pp LPP20BK21NA

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.