

Technical Data Sheet

Ferro Pp LPP40BC47WH

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 42% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Good Impact Resistance	• Heat Stabilized	• Homopolymer
Uses	• Protective Coverings		
Appearance	• White		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.27	1.27 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3400 psi	23.4 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	30 %	30 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	328000 psi	2260 MPa	
Tangent : 73°F (23°C)	404000 psi	2790 MPa	
Flexural Strength (73°F (23°C))	6000 psi	41.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.80 ft·lb/in	43 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	20 ft·lb/in	1100 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	135 in·lb	15.3 J	ASTM D5420
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	75	75	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	
264 Psi (1.8 Mpa), Unannealed	155 °F	68.3 °C	

Technical Data Sheet

Ferro Pp LPP40BC47WH

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	395 to 400 °F	202 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 415 °F	210 to 213 °C
Nozzle Temperature	415 to 425 °F	213 to 218 °C
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa

Notes

These are typical property values not to be construed as specification limits.