

Technical Data Sheet

Ferro Pp NPP00GW31

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Additive	• Impact Modifier
Features	• Impact Modified
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	4500 psi	31.0 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	50 %	50 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	195000 psi	1340 MPa	
Tangent : 73°F (23°C)	206000 psi	1420 MPa	
Flexural Strength (Yield, 73°F (23°C))	6000 psi	41.4 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.5 ft·lb/in	80 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact	280 in·lb	31.6 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	235 °F	113 °C	
264 Psi (1.8 Mpa), Unannealed	140 °F	60.0 °C	
RTI Elec (0.06 In (1.6 Mm))	149 °F	65.0 °C	UL 746B
RTI Imp (0.06 In (1.6 Mm))	149 °F	65.0 °C	UL 746B
RTI Str (0.06 In (1.6 Mm))	149 °F	65.0 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.0025 In (0.063 Mm))	HB	HB	UL 94

Technical Data Sheet

Ferro Pp NPP00GW31

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.