

## Technical Data Sheet

### Hifax CA 1110 G2 HF C11306



Polypropylene Compounds

#### Product Description

Hifax CA 1110 G2 HF C11306 is a 12% talc filled PP copolymer, with high melt flow, good impact resistance and very good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11306 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Automotive Parts; Bumpers; Exterior Trim
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1300	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	16	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (-30 °C)	4.9	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	111	°C	ISO 306