

Technical Data Sheet

Hifax SP179X T 2003 (SC BLACK)



Polypropylene Compounds

Product Description

Hifax SP179X T 2003 is an unfilled polypropylene copolymer, with medium melt flow rate and high impact resistance. Product is available as non color matched, black, pellet form.

Regulatory Status

For regulatory compliance information, see Hifax SP179X T 2003 (SC BLACK) [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific
Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Impact Resistance; Medium Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	1100	MPa	ISO 178
Tensile Stress at Yield	18	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	50	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	75	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.