(+) 188 1699 6168 hongrunplastics.com

# **Technical Data Sheet**

# Hifax TKC 220P G12761

Polypropylene Compounds



### **Product Description**

*Hifax* TKC 220P G12761 is a 15% talc filled PP copolymer, with high impact resistance and outstanding scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G12761 color version.

#### **Regulatory Status**

For regulatory compliance information, see *Hifax* TKC 220P G12761 <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status Commercial: Active

Availability Europe
Application Bumpers
Market Automotive

Processing Method Injection Molding

Attribute High Impact Resistance; Scratch Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	14	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1400	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	50	kJ/m²	ISO 179-1/1eA
(-40 °C)	3	kJ/m²	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	45	kJ/m²	ISO 180/1A
(-40 °C)	4	kJ/m²	ISO 180/1A
Thermal		·	
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2

## Notes

These are typical property values not to be construed as specification limits.