

Technical Data Sheet

Hifax TRC 412P C12594



Polypropylene Compounds

Product Description

Hifax TRC 412P C12594 is a 20% talc filled PP copolymer, with high flowability, high stiffness and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C12594 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	30	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	25	kJ/m ²	ISO 179-1/1eA
(-30 °C)	4	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	135	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2