

Technical Data Sheet

Hifax TRC 495P G13076



Polypropylene Compounds

Product Description

Hifax TRC 495P G13076 is a 16% talc filled PP copolymer, with superior impact/stiffness balance, excellent flowability, good processability and good UV resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in G13076 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1