

Technical Data Sheet

Hifax TRC 779P LD C1 C25119



Polypropylene Compounds

Product Description

Hifax TRC 779P LD C1 C25119 is high melt flow, 1,600 MPa flexural modulus, UV-stabilized, paintable, 13% mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed for use in multiple automotive exterior applications.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Bumpers; Exterior Automotive Applications; Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Excellent Processability; Good UV Resistance; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C)	1600	MPa	ISO 178
Tensile Strength, (23 °C)	16	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	45	kJ/m ²	ISO 180
(-30 °C)	5.5	kJ/m ²	ISO 180