

Technical Data Sheet

Hifax TYC 459P C1 3004



Polypropylene Compounds

Product Description

Hifax TYC 459P C1 3004 is a 21% talc filled PP copolymer, with very low shrinkage, high flowability, good impact/stiffness balance and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 3004 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good UV Resistance; High Flow; High Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	30	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	21	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	30	kJ/m ²	ISO 180/1A
(-30 °C)	3.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75A-1, -2