

Technical Data Sheet

Hifax TYC 852P E C11462



Polypropylene Compounds

Product Description

Hifax TYC 852P E C11462 is a 22% talc filled PP copolymer, with high flowability, high impact resistance and low CLTE. Product is available as a customized color matched, pellet form. This grade is delivered in C11462 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow; High Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	31	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	45	kJ/m ²	ISO 179-1/1eA
(-40 °C)	3.5	kJ/m ²	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	40	kJ/m ²	ISO 180/1A
(-40 °C)	4	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	100	°C	ISO 75B-1, -2