

Technical Data Sheet

Hifax TYS 699P BLACK



Polypropylene Compounds

Product Description

Hifax TYS 699P BLACK is an unfilled impact modified polypropylene, with very high melt flow rate offering an excellent impact/stiffness balance.

Product is available as non color matched, black, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	90	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.89	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	900	MPa	ISO 178
Tensile Stress at Yield	15.5	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	35	kJ/m ²	ISO 180/1A
(-30 °C)	6.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2