

Technical Data Sheet

Ferrex GPP25CG65WH

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

General		
Filler / Reinforcement	• Calcium Carbonate, 25% Filler by Weight	
Features	• High Gloss	• Homopolymer
Forms	• Pellets	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.08	1.08 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	20 g/10 min	20 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	4100 psi	28.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	55 %	55 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	247000 psi	1700 MPa	
Tangent : 73°F (23°C)	263000 psi	1810 MPa	
Flexural Strength (Yield, 73°F (23°C))	6200 psi	42.7 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.0 ft·lb/in	53 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	13 ft·lb/in	690 J/m	ASTM D4812
Gardner Impact	100 in·lb	11.3 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	62.8 °C	

Additional Information			
Filler Content, ASTM D2584: 25.5%			

Notes

These are typical property values not to be construed as specification limits.