

Technical Data Sheet

Ferro Pp LPP30BC94BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Calcium Carbonate, 30% Filler by Weight
Additive	• UV Stabilizer
Features	• Homopolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.5 g/10 min	8.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	4000 psi	27.6 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	35 %	35 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	292000 psi	2010 MPa	
Tangent : 73°F (23°C)	335000 psi	2310 MPa	
Flexural Strength (Yield, 73°F (23°C))	6400 psi	44.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.60 ft·lb/in	32 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	10 ft·lb/in	530 J/m	ASTM D4812
Gardner Impact	45.0 in·lb	5.08 J	ASTM D5420


Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	235 °F	113 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	62.8 °C	

Additional Information	
Filler Content, ASTM D2584: 30%	

Technical Data Sheet

Ferro Pp LPP30BC94BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.