

Technical Data Sheet

Ferro Pp LPP40BC15NA


Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 40% Filler by Weight		
Features	• Homopolymer		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.27	1.27 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3500 psi	24.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	30 %	30 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	345000 psi	2380 MPa	
Tangent : 73°F (23°C)	431000 psi	2970 MPa	
Flexural Strength (73°F (23°C))	6100 psi	42.1 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.70 ft·lb/in	37 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	16 ft·lb/in	830 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	65.0 in·lb	7.34 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	255 °F	124 °C	
264 Psi (1.8 Mpa), Unannealed	165 °F	73.9 °C	

Technical Data Sheet

Ferro Pp LPP40BC15NA

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.