

Technical Data Sheet

Ferro Pp LPP40YR06HB

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Calcium Carbonate, 40% Filler by Weight
Features	• Homopolymer
Appearance	• White
Forms	• Pellets
Processing Method	• Injection Molding


Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.22	1.22 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	2000 psi	13.8 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	150 %	150 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	143000 psi	986 MPa	
Tangent : 73°F (23°C)	158000 psi	1090 MPa	
Flexural Strength (Yield, 73°F (23°C))	3100 psi	21.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	13 ft·lb/in	670 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact	245 in·lb	27.7 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	175 °F	79.4 °C	
264 Psi (1.8 Mpa), Unannealed	120 °F	48.9 °C	

Additional Information	
Filler Content, ASTM D2584: 37.5%	

Technical Data Sheet

Ferro Pp LPP40YR06HB

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.