

Technical Data Sheet

Ferro Pp LPP50BC73NA


Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 52% Filler by Weight		
Features	• Homopolymer		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.39	1.39 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	11 g/10 min	11 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	2900 psi	20.0 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	35 %	35 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	361000 psi	2490 MPa	
Tangent : 73°F (23°C)	483000 psi	3330 MPa	
Flexural Strength (73°F (23°C))	5200 psi	35.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.50 ft·lb/in	27 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	13 ft·lb/in	690 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	110 in·lb	12.4 J	ASTM D5420
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	74	74	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	
264 Psi (1.8 Mpa), Unannealed	150 °F	65.6 °C	

Technical Data Sheet

Ferro Pp LPP50BC73NA

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	395 to 400 °F	202 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 415 °F	210 to 213 °C
Nozzle Temperature	415 to 425 °F	213 to 218 °C
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa

Notes

These are typical property values not to be construed as specification limits.