

Technical Data Sheet

Ferro Pp TPP40AE57BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General		
Filler / Reinforcement	• Talc, 40% Filler by Weight	
Additive	• Heat Stabilizer	
Features	• Heat Stabilized	• Homopolymer
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.25	1.25 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	7.0 g/10 min	7.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	5000 psi	34.5 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	5.0 %	5.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	480000 psi	3310 MPa	
Tangent : 73°F (23°C)	641000 psi	4420 MPa	
Flexural Strength (Yield, 73°F (23°C))	8400 psi	57.9 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.40 ft·lb/in	21 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	4.8 ft·lb/in	260 J/m	ASTM D4812
Gardner Impact	7.00 in·lb	0.791 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	285 °F	141 °C	
264 Psi (1.8 Mpa), Unannealed	185 °F	85.0 °C	

Additional Information			
Filler Content, ASTM D2584: 39.5%			

Technical Data Sheet

Ferro Pp TPP40AE57BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.