

Technical Data Sheet
Fiberfil® J-60/20/FR
Polypropylene Homopolymer
Engineering Plastics




General			
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Flame Retardant • Homopolymer		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.42	1.42 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow			ASTM D955
0.125 in (3.18 mm)	2.0E-3 in/in	0.20 %	
0.250 in (6.35 mm)	2.0E-3 in/in	0.20 %	
Water Absorption (24 hr)	0.020 %	0.020 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	900000 psi	6210 MPa	ASTM D638
Tensile Strength (73°F (23°C))	10500 psi	72.4 MPa	ASTM D638
Tensile Elongation (Yield, 73°F (23°C))	3.0 %	3.0 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	800000 psi	5520 MPa	ASTM D790
Flexural Strength (73°F (23°C))	14000 psi	96.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 in (3.18 mm)	1.5 ft·lb/in	80 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-Scale)	100 to 110	100 to 110	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	310 °F	154 °C	
264 psi (1.8 MPa), Unannealed	300 °F	149 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94

Technical Data Sheet

Fiberfil® J-60/20/FR

Polypropylene Homopolymer
Engineering Plastics

lyondellbasell



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	170 °F	77 °C
Drying Time	2.0 hr	2.0 hr
Suggested Max Moisture	0.20 %	0.20 %
Rear Temperature	390 to 410 °F	199 to 210 °C
Middle Temperature	400 to 440 °F	204 to 227 °C
Front Temperature	360 to 390 °F	182 to 199 °C
Nozzle Temperature	360 to 380 °F	182 to 193 °C
Processing (Melt) Temp	390 to 450 °F	199 to 232 °C
Mold Temperature	90 to 160 °F	32 to 71 °C
Injection Rate	Moderate	Moderate
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa

Injection Notes

Screw speed: Medium

Notes

These are typical property values not to be construed as specification limits.