

Technical Data Sheet

Gapex APP30GP06GY

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass\Mineral, 30% Filler by Weight		
Features	• Homopolymer		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.11	1.11 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	16 g/10 min	16 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	6400 psi	44.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	5.0 %	5.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	467000 psi	3220 MPa	
Tangent : 73°F (23°C)	509000 psi	3510 MPa	
Flexural Strength (Yield, 73°F (23°C))	9200 psi	63.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.70 ft·lb/in	37 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	6.7 ft·lb/in	360 J/m	ASTM D4812
Gardner Impact	20.0 in·lb	2.26 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	
Additional Information			
Filler Content, ASTM D2584: 26.5%			

Notes

These are typical property values not to be construed as specification limits.