

Technical Data Sheet

Gapex APP40GR46BK

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

General			
Filler / Reinforcement	• Glass\Mineral, 40% Filler by Weight		
Features	• Chemically Coupled		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.25	1.25 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	7900 psi	54.5 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	3.0 %	3.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	639000 psi	4410 MPa	
Tangent : 73°F (23°C)	760000 psi	5240 MPa	
Flexural Strength (73°F (23°C))	12800 psi	88.3 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.0 ft·lb/in	53 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	5.3 ft·lb/in	280 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	2.80 in·lb	0.316 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	280 °F	138 °C	

Additional Information

Testing and measurements were performed at 73 +/-3°F and 50 +/-5% relative humidity unless otherwise noted.

Notes

These are typical property values not to be construed as specification limits.