

Technical Data Sheet

Gapex RPP35EC15BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight		
Features	• Chemically Coupled • Homopolymer		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.19	1.19 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	12000 psi	82.7 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	3.0 %	3.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	925000 psi	6380 MPa	
Tangent : 73°F (23°C)	983000 psi	6780 MPa	
Flexural Strength (Yield, 73°F (23°C))	17700 psi	122 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.4 ft·lb/in	75 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	7.7 ft·lb/in	410 J/m	ASTM D4812
Gardner Impact	2.00 in·lb	0.226 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	320 °F	160 °C	
264 Psi (1.8 Mpa), Unannealed	305 °F	152 °C	
Additional Information			
Filler Content, ASTM D2584: 36.5%			

Technical Data Sheet

Gapex RPP35EC15BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.