

Technical Data Sheet

Icorene N4420

Polypropylene Homopolymer
LyondellBasell Industries
Custom Powders

Product Description

ICORENE® N4420 is a polypropylene homopolymer with a high fluidity.

This grade is suitable for injection moulding and masterbatch applications. It's main applications are thin walled packaging items or housewares.

General

Features	• High Flow	• Homopolymer	
Uses	• Compounding	• Masterbatch	• Thin-walled Packaging
Agency Ratings	• EU Food Contact	• FDA Food Contact	
Forms	• Powder		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	25 g/10 min	25 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4640 psi	32.0 MPa	ASTM D638
Tensile Elongation (Yield)	9.0 %	9.0 %	ASTM D638
Flexural Modulus	181000 psi	1250 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	0.71 ft·lb/in ²	1.5 kJ/m ²	ISO 179/1eA
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	69	69	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	174 °F	79.0 °C	ISO 75-2/B

Notes

These are typical property values not to be construed as specification limits.