

Technical Data Sheet
Lucent PP GPP-130
Polypropylene Homopolymer
Engineering Plastics



Product Description

30% Glass Fiber Reinforced, Chemically Coupled, Homopolymer Polypropylene

Melt Flow Adjustable for Application

Colors Available

Add "U" for UV Stabilized

Add "H" for Heat Stabilized

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Chemically Coupled	• Homopolymer	
Automotive Specifications	• TOYOTA TSM 5601G-1		
Appearance	• Colors Available		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	4.0E-3 in/in	0.40 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11000 psi	75.8 MPa	ASTM D638
Tensile Elongation (Break)	4.0 %	4.0 %	ASTM D638
Flexural Modulus	675000 psi	4650 MPa	ASTM D790
Flexural Strength	15700 psi	108 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	1.2 ft-lb/in	64 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	285 °F	141 °C	

Notes

These are typical property values not to be construed as specification limits.