

Technical Data Sheet

Matrixx SPR3B35CCBK21

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Product Description

35% percent glass/mineral filled, heat stabilized, polypropylene

General

Filler / Reinforcement	• Glass\Mineral, 35% Filler by Weight
Features	• Medium Impact Resistance
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.17	1.17 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	8300 psi	57.2 MPa	ASTM D638
Tensile Elongation (Break)	6.0 %	6.0 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	640000 psi	4410 MPa	ASTM D790
Flexural Strength (Yield)	12700 psi	87.6 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 In (3.18 Mm)	2.3 ft-lb/in	120 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	70	70	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	

Additional Information

Melt Flow Rate, ASTM D1238: 0-7 g/10min

Technical Data Sheet

Matrixx SPR3B35CCBK21

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	350 to 430 °F	177 to 221 °C
Middle Temperature	350 to 430 °F	177 to 221 °C
Front Temperature	350 to 430 °F	177 to 221 °C
Processing (Melt) Temp	390 to 440 °F	199 to 227 °C
Mold Temperature	70 to 120 °F	21 to 49 °C
Injection Rate	Moderate	Moderate
Back Pressure	20.0 to 300 psi	0.138 to 2.07 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Drying not normally required
Injection Booster Pressure: Maximum without flash, 60% of machine maximum, target
Screw Speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.