

Technical Data Sheet

Moplen HP500N



Polypropylene, Homopolymer

Product Description

Moplen HP500N is a homopolymer used for general purpose injection moulding applications. It exhibits good flow and stiffness. Moplen HP500N is suitable for food contact.

Moplen HP500N is UL listed under file E31765

Application	Furniture; Housewares
Market	Compounding; Consumer Products; Rigid Packaging
Processing Method	Compounding; Injection Blow Molding
Attribute	Medium Flow; Medium Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1400	MPa	ISO 527-1, -2
Tensile Stress at Yield	35	MPa	ISO 527-1, -2
Tensile Strain at Break	> 50	%	ISO 527-1, -2
Tensile Strain at Yield	10	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature			
(A/50)	153	°C	ISO 306
(B50)	85	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2