

Technical Data Sheet

Moplen HP552N



Polypropylene, Homopolymer

Product Description

Moplen HP552N is a polypropylene homopolymer used for extrusion applications. *Moplen* HP552N is formulated with an anti-gasfading stabilisation package. *Moplen* HP552N is used for the production of continuous filaments and fine denier staple fibres. Typical applications are carpets and nonwovens.

This grade is not intended for medical and pharmaceutical applications.

Application	Filament Yarn; Hygiene Nonwoven; Nonwovens
Market	Textile
Processing Method	Continuous Filament/Spinning; Fibers; Staple Fiber
Attribute	Gas-fading Resistant; Homopolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	13	g/10 min	ISO 1133-1
Density	0.900	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1400	N/mm ²	ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)	23	N/mm ²	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	34	N/mm ²	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	700	%	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	11	%	ISO 527-1, -2
Thermal			
Vicat Softening Temperature, (A50)	154	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	85	°C	ISO 75B-1, -2