(+) 188 1699 6168 hongrunplastics.com



## Moplen HP563S

## Polypropylene, Homopolymer

## **Product Description**

Moplen HP563S is a polypropylene homopolymer manufactured using the Spheripol process. Its has excellent drawability and spinnability properties, and is particularly suitable for production of fine denier spunbond non-wovens. Potential end use applications include diapers and sanitary napkins, apparel covers, wet tissues, shopping bags and agricultural-use textiles. Moplen HP563S can be evaluated in applications that need Anti-Gas Fading performance.

## **Product Characteristics**

Test Method used ASTM

Processing Methods Continuous Filament/Spinning, Spun Bond

Features Gas-fading Resistant, Homopolymer, Narrow Molecular

Weight Distribution

**Typical Customer Applications** Hygiene Nonwoven, Wipes/Tissues

| Typical Properties                        | Method      | Value | Unit     |
|---|-------------|-------|----------|
| Physical                                  |             |       |          |
| Melt Flow Rate (230°C/2.16kg)             | ASTM D 1238 | 38    | g/10 min |
| Note: ASTM D1238L                         |             |       |          |
| Density                                   | ASTM D 1505 | 0.9   | g/cm³    |
| Mechanical                                |             |       |          |
| Flexural Modulus                          | ASTM D 790  | 15000 | kg/cm²   |
| Tensile Strength @ Yield                  | ASTM D 638  | 380   | kg/cm²   |
| Tensile Elongation @ Yield                | ASTM D 638  | 8     | %        |
| Impact                                    |             |       |          |
| Notched Izod Impact (23 °C)               | ASTM D 256  | 3     | kg-cm/cm |
| Hardness                                  |             |       |          |
| Rockwell Hardness (R Scale)               | ASTM D 785  | 98    |          |
| Thermal                                   |             |       |          |
| Heat deflection temperature at 0.46 N/mm2 | ASTM D 648  | 100   | °C       |