

Technical Data Sheet

Moplen PP567P



Polypropylene, Homopolymer

Product Description

Moplen PP567P is a polypropylene homopolymer used for extrusion applications. *Moplen* PP567P has a very narrow molecular weight distribution and is formulated with an anti-gasfading stabilisation package. *Moplen* PP567P is used for the production of continuous filaments. Typical applications are high-tenacity yarns and spunbond nonwovens.

This grade is not intended for medical and pharmaceutical applications.

Application	Absorption & Filtration; Bulk Continuous Filament & Continuous Filament; Filament Yarn; Geotextile & Agriculture; Hygiene Nonwoven; Nonwovens; Wipes/Tissues
Market	Textile
Processing Method	Continuous Filament/Spinning; Fibers; Spunbond
Attribute	Controlled Rheology; Gas-fading Resistant; Homopolymer; Narrow Molecular Weight Distribution

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density	0.900	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1300	N/mm ²	ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)	21	N/mm ²	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	33	N/mm ²	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	700	%	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	11	%	ISO 527-1, -2
Thermal			
Vicat Softening Temperature, (A50)	153	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	85	°C	ISO 75B-1, -2