

Technical Data Sheet

Polyfort PPH MT25 H-1737

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Product Description

PPH MT25H-1737 is a 25% Talc-Filled, NSF Grade Polypropylene, Homopolymer

General

Filler / Reinforcement	• Talc, 25% Filler by Weight
Appearance	• Colors Available
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.6 g/10 min	5.6 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength	5070 psi	34.9 MPa	ASTM D638
Flexural Modulus - Tangent	426000 psi	2940 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact	9.1 ft·lb/in	480 J/m	ASTM D4812

Technical Data Sheet

Polyfort PPH MT25 H-1737

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.