

Technical Data Sheet

Polyfort FPP 40 T LE K2274 BLK



Polypropylene, Homopolymer

Product Description

40% talc filled PP homopolymer, low emission

Processing Method	Injection Molding
Attribute	Homopolymer; Low Emissions
Filler/Reinforcement	Talc, 40%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (230 °C/2.16 kg)	6.0	cm ³ /10 min	ISO 1133
Density, (Method A)	1.26	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	30.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.0	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	3600	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	21	kJ/m ²	ISO 179
Hardness			
Ball Indentation Hardness, (H 358/30)	73.0	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	97.0	°C	ISO 306
(A (10N), 50 °C/h)	158	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	128	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	76.0	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*cm	IEC 60093
Surface Resistivity	>1.0E+15	ohm	IEC 60093
UL Information			
Flammability Classification			
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	220 to 260	°C
Mold Temperature	30 to 60	°C