

Technical Data Sheet

Polyfort FPP5B30CCNANAT



Polypropylene, Homopolymer

Product Description

Polyfort FPP5B30CCNANAT is a Polypropylene Homopolymer Glass Fiber, 30% filled material and is typically used in Injection Molding applications. Features include: Homopolymer, and Ultra High Impact Resistance.

Processing Method	Injection Molding
Attribute	Homopolymer; Ultra High Impact Resistance
Forms	Pellets
Filler/Reinforcement	Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate	9.5	g/10 min	ASTM D1238
Density - Specific Gravity	1.13	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (23 °C)	46.2	MPa	ASTM D638
Flexural Modulus, (Tangent)	3720	MPa	ASTM D790
Impact			
Gardner Impact	3.39	J	ASTM D3029
Notched Izod Impact, (23 °C, 3.18 mm)	210	J/m	ASTM D256
Hardness			
Durometer Hardness, (Shore D)	75		ASTM D2240
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	116	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	127	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Screw Speed	20 to 60	rpm
Processing (Melt) Temp	199 to 243	°C
Front Temperature	199 to 243	°C
Middle Temperature	199 to 243	°C
Rear Temperature	199 to 243	°C
Injection Rate	Moderate	
Back Pressure	<0.345	MPa
Mold Temperature	16 to 66	°C
Cushion	6.35 to 12.7	mm