(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

## Pro-fax HP659S

Polypropylene, Homopolymer



## **Product Description**

*Pro-fax* HP659S polypropylene homopolymer is available in pellet form. This resin is typically used in spunbond and continuous filament applications that require superior spinnability, finer fibers and good color stability. *Pro-fax* HP659S is also used in extrusion coating and cast film applications. This product is produced with a catalyst system that does not include intentionally added phthalates.

**Application** Geotextile & Agriculture; Hygiene Film; Hygiene Nonwoven; Protective Clothes;

Textile Packaging Film; Wipes/Tissues

Market Flexible Packaging; Textile

Processing Method Cast Film; Extrusion Coating; Injection Molding; Spunbond

Attribute Gas-fading Resistant; Good Processing Stability; Narrow Molecular Weight

Distribution

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	35	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	ASTM D792