(+) 188 1699 6168 hongrunplastics.com

Technical Data Sheet

Hostacom BB 1161 F/M 2678

Polypropylene Compounds

Product Description

Hostacom BB 1161 F/M 2678 is a 12% talc filled PP copolymer, with high melt flow, excellent processability, high stiffness and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2678 color version.

Regulatory Status

For regulatory compliance information, see *Hostacom* BB 1161 F/M 2678 <u>Product Stewardship Bulletin (PSB)</u> and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status Commercial: Active

Availability Europe

Application Interior Trims

Market Automotive

Processing Method Injection Molding

Attribute Good Color Stability; Good Processability; High Flow; Medium Impact Resistance; UV

Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	28	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	106	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

