

Technical Data Sheet

Hostacom BFR



Polypropylene Compounds

Product Description

Hostacom BFR is talc filled PP copolymer , with medium impact/stiffness balance and good flowability.
The grade contains up to 25% PI Recyclate.

Regulatory Status

For regulatory compliance information, see Hostacom BFR [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Underhood
Market	Automotive
Processing Method	Injection Molding
Attribute	Medium Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23 °C)	0.95	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	900	MPa	ISO 178/A1
Impact			
Notched Izod Impact Strength, (23 °C)	15	kJ/m ²	ISO 180/1A

Notes

These are typical property values not to be construed as specification limits.