

Technical Data Sheet

Hostacom DG 154 2 G62760



Polypropylene Compounds

Product Description

Hostacom DG 154 2 G62760 is a 13% talc filled PP copolymer. Product is available as a customized color matched, pellet form. This grade is delivered in G62760 color version.

Regulatory Status

For regulatory compliance information, see Hostacom DG 154 2 G62760 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; High Flow; Low Density; Medium Impact Resistance; Medium Stiffness; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
Impact			
Notched Izod Impact Strength, (23 °C)	4	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	123	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	58	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.