

## Technical Data Sheet

### Hostacom DG 154/2 C13084

Polypropylene Compounds

#### Product Description

Hostacom DG 154/2 C13084 is a 13% talc filled PP copolymer, with high melt flow rate and good rigidity. The product is available in different color matched, pellet form. This grade is delivered in C13084 color version.

#### Regulatory Status

For regulatory compliance information, see Hostacom DG 154/2 C13084 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Processability; High Flow; Low Density; Medium Impact Resistance; Medium Stiffness; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	4	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	123	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	58	°C	ISO 75A-1, -2

#### Notes

These are typical property values not to be construed as specification limits.