(+) 188 1699 6168 hongrunplastics.com

Technical Data Sheet

Hostacom DYS707N HS1 NAT

Polypropylene Compounds

Product Description

Hostacom DYS707N HS1 NAT is an unfilled, impact modified grade that is typically used for automotive pillar applications that require excellent impact/stiffness balance, good flowability, and excellent impact performance at low temperature.

Application Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Good Impact Resistance; Good Stiffness; Low Temperature Impact Resistance

Typical Properties	Nominal	Units	Test Method
	Value		
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	17	g/10 min	ISO 1133-1
Density	0.90	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	950	MPa	ISO 178
Tensile Stress at Yield	17	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	70	kJ/m²	ISO 179
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.

